



PROTECTIVE

PAINTS

Protective Paints Limited, 14B Arwen Place, East Tamaki, PO Box 204293, Highbrook Postal Centre, Manukau 2161
Ph: (09) 274 5606 Ph: 0800 724 684 Fax: (09) 274 0940 Email: reception@propaints.co.nz Website: www.propaints.co.nz

210-100

Duratrade Acrylic Gloss White

For use on interior/exterior walls, timber, etc. and on exterior masonry and concrete surfaces.

PRODUCT FEATURES

- High gloss
- High opacity
- Excellent exterior performance
- Ease of application
- Wide colour range

CHECKLIST

Quality	Professional
Int/Ext	Both
Gloss Level	80 at 60°
Wet Areas	No
Primer Required	Yes
Wash Up	Water
Colour	White and bases tintable to a range of pastel colours. Test and approve colour before you start.

ESTIMATION

Pack Size	4L, 10L
Appearance When Dry	High Gloss
Storage Temperature	10°C - 50°C
Shelf Life (months)	18
Toxicity	Formulated without lead or mercury
Percentage by Weight	47%
Volume Solids	38%
Wet Film Thickness	80-100 microns per coat
Dry Film Thickness	28-36 microns per coat
Pot life (@25°C)	One pack
Mixing:	Thoroughly stir with a broad paddle to ensure product is fully incorporated. When using tinted material check colour is correct prior to use.
Spread Rate	10-12sqm/L

SURFACE PREPARATION

Interior: Apply over Duratrade Alkyd Pigmented Sealer/Undercoat (8352-100) or Duratrade Acrylic Easy Sand Sealer (218-100). Lightly sand to ensure a smooth even surface. When repainting existing acrylic finishes ensure that surface is thoroughly cleaned. Check to confirm adhesion of the previous coating is sound before proceeding.

Exterior Masonry: Clean by water blasting or other suitable method to remove all dirt, dust, mould, lichen, loose and flaky paint etc. Mould should be treated with Mouldkill X200 (A924) solution and completely removed. For new concrete or polymer concrete substrates refer to Modocryl (A531). Masonry must be 28 days old prior to painting.

APPLICATION

Min Steel Temperature:	N/A
Max Relative Humidity:	75%
Temperature Range:	10°C-35°C

Methods:

Brush, Roller, Airless Spray

Prepare as above and apply 2 coats of Duratrade Acrylic Gloss White.

Thinners:	Water
Cleaning Solvent:	Water
Max. Volume Thinners	5%
Nozzle Orifice:	11 – 15 Thou Airless Spray
Fan Angle:	30° - 50°
Nozzle Pressure:	2500psi

DRYING CHARACTERISTICS

(20°C, 50% RH)

Touch	1 hour
Full Dry	12 hours
Recoat	4 hours. For best results allow overnight dry between coats.

SPECIAL PRECAUTIONS – Health and Safety AB20

Do not take internally. Avoid contact with eyes and prolonged contact with skin or breathing of spray mist. Use a dust/particulate respirator while spraying or sanding. Close containers after each use. USE COMPLETELY OR DISPOSE OF PROPERLY. Hold unused paint in sealed container for special waste disposal. Do not discard into sewers or waterways.

USE ONLY WITH ADEQUATE VENTILATION
KEEP OUT OF REACH OF CHILDREN

FIRST AID

If Swallowed: Give water to dilute and get medical advice.

Eye Contact: Treat immediately with plenty of running water. Get medical attention if irritation persists.

Breathing Difficulty: Leave the area immediately to obtain fresh air. Get medical attention if problem persists.
For further information, see the Health and Safety Data Sheet for this product.

This information is intended to give a fair description of the product and its capabilities under specific test conditions. It does not constitute an offer by the manufacturers nor do they warrant or guarantee its accuracy or completeness in describing the performance or suitability of the product.

For further technical information please phone 0800 724 684

ISSUE NUMBER: 210-100 (V3)

ISSUE DATE: 19 May 2016